



Oftalmologisk Selskap i Oslo



Che John Connon

This article is a summary of the Oslo Society of Ophthalmology Honorary Lecture 2019 delivered by Professor Connon. Oslo Society of Ophthalmology, established in 1915, invites outstanding scientists four times a year to give lectures. Selected presentations are published in *Oftalmolog*.

Corneal tissue engineering: a personal perspective

CHE JOHN CONNON, PROFESSOR OF TISSUE ENGINEERING, NEWCASTLE UNIVERSITY, UNITED KINGDOM

There persists a growing and urgent need for engineered corneal tissue. We have taken an early lead on engineering cell-contrived corneal tissue i.e. controlling the inherent ability of corneal stromal cells to self-assemble and produce a collagen rich corneal stromal tissue - a mimic. We have dubbed this *in vitro* approach "tissue-templating". Central to this method is the axiom, 'where cells lead collagen follows'. Within this short article I will briefly outline the journey we have taken, key milestones and what the future may hold for corneal tissue engineering.

Within the field of corneal tissue engineering numerous attempts have been made to construct stromal tissue equivalents and with varying degrees of success, led by the seminal work of May Griffith et al¹ (and reviewed here²). These studies have previously focused

on creating materials with appropriate levels of transparency, cell compatibility and mechanical strength. Despite the significance of these achievements few have yet addressed a critical quality - a cornea's shape and thereby its optical strength. An incorrectly shaped corneal construct would cause light to be focused either in front or behind the retina and thus the engineering of such a living tissue that can perform this function is, we believe, a key milestone in the development of a tissue engineered cornea.

The approach we have taken to create a functional tissue engineered cornea has been reductionist. We have endeavored, over the last 20 years, to build on the previous work of others and further improve our understanding of the biology of the cornea at a molecular, cellular and tissue level. We have taken this new understanding and looked to

apply it in some novel manner in order to improve our tissue engineering of a functional cornea.

For example, we have quantified the nanostructure of the cornea and related this arrangement to the preservation of corneal transparency^{3,4}, we subsequently applied these measurements to the design of new corneal biomaterials capable of supporting both corneal stromal and epithelial cell self-assembly, differentiation and growth⁵. More recently we have shown how cell-derived hierarchical collagen organisation can be modulated or prescribed by the precise spatio-temporal positioning of corneal stromal cells upon a 2D surface^{6,7} (Figure 1). Further studies have shown that by controlling the amount of initial cell alignment collagenous tissues




Figure 1. Corneal stromal cells extracted from human limbal tissue and grown in serum free conditions readily respond to an aligned template.

ensue with predictable distinctions in structure and function⁸.

This early work strengthened our hypothesis that proper organisation of cells and extracellular matrix (ECM) over multiple length scales is a prerequisite for proper organ function; indeed, within the cornea it is fundamental to its transparency⁹. To address this critical concept tissue engineers have traditionally utilised *top-down* approaches where cells are seeded into artificial¹⁰ or bio-derived scaffolds¹¹ to provide them with a structural guidance to support

the desired tissue organisation and shape. However, we and others have more recently explored the *bottom-up* assembly of cells to induce the formation of tissues with various microengineered geometries, which in turn offers improved function and/or greater control of tissue structure when compared with engineered structures using a top-down approach^{8,12,13} (Figure 2).

A bottom-up approach is potentially much more powerful than a top-down approach as it works on the principle that if fully functional tissues can

be generated from cell populations during normal development then that these cells can reenact this in vitro if given appropriate growth conditions. Thus, the final tissues have the correct structure and function driven by appropriate nanoscale resolution of the ECM and proper spatial positioning and differentiation of the component cells. We believe that this level of organization is not possible, or at least not commercially scalable, with current top-down approaches to tissue engineering.

We achieve bottom-up or cell derived tissue formation using a cell culture technique we have called “tissue-templating”. Our first demonstration of this approach was the use of aligned cell binding motifs patterned on to a glass slide⁶. Growth of corneal stromal cells upon this surface resulted in highly aligned cells. Moreover, these aligned cells then produced similarly aligned fibrillar collagen⁷. Intriguingly as the cells continued to grow and stratify they would do so perpendicular to the layer below and with thick layer of aligned collagen between them. This created tissue with similar hierarchical structures (orthogonal placed layers of bundled collagen fibrils i.e. lamellae) to the tissue from which the cells were initially taken i.e. the




Figure 2. Mixing cells with a material such as collagen often results in a simple tissue, lacking order and proper function (top-down). However, using a phenotypic cell type under specific direction creates highly organized growth and extracellular matrix production resulting in a complex tissue with enhanced functionality (bottom-up).

cornea⁸. An assumption underlying such an approach is that the spatial organisation, initially imposed by artificial environments (template), is basically preserved throughout the tissue remodeling phases.

Whilst much of our earlier studies were performed using 2D templates to drive cell organisation and subsequent tissue organisation, some work has also been carried out using 3D templates. For example, we have shown that template curvature influences cell alignment to create improved human corneal equivalents¹⁴ and that 3D bioprinting of a corneal stroma equivalent is possible¹⁵. Recent work has also been performed in 4D tissue engineering¹⁶.

Within a 4D approach, the additional dimension is time, thus it is possible to create a template environment for corneal stromal cells that breaks away from the assumption stated above (that templated spatial organization is preserved throughout the process) i.e. that cells change their organization

during the culture period and a time resolved tissue ensues. To demonstrate this, we created flat/planar collagen gels comprising stromal cells with a spatially differentiated bio-chemical cue. The localized interaction with these cues brought about regional differences in cell behavior, namely contraction, which resulted in the planar tissue forming a curved corneal-like tissue over 5 days in culture.

Looking forward we believe tissue-templating holds great promise as a scalable means to generate environments for corneal cells to grow from, (i.e. the manufacture of proto-corneas that mature either inside or outside the body) and into functional corneal replacements. Whilst much of our work has been focused on only one part of the cornea, the stroma, we argue that the stroma itself is a natural template upon which the remaining corneal cells can react. For example, we have recently shown that stromal stiffness affects corneal epithelial cell

differentiation and that modulating corneal tissue biomechanics can restore limbal stem cell function following pathological stiffening of the stroma (i.e. chemical burn)¹⁷. Moreover, from a tissue engineering perspective we have shown that it is possible to template stromal cells, within a single construct, to produce an ECM with different and precise levels of stiffness. Such constructs were then shown to support epithelia growth at corresponding levels of differentiation e.g. undifferentiated at the circumference and differentiated at the centre across its surface¹⁶.

In summary, much has been achieved in a relatively short period of time and it is my contention that the cornea, because of its unique physiology, will be one of the first routinely transplanted tissue engineered therapeutic products and that we will see this within the next decade.

References: www.oftalmolog.com ■

References

1. Griffith M, Osborne R, Munger R, Xiong X, Doillon CJ, Laycock NLC, Hakim M, Song Y, Watsky MA (1999) Functional Human Corneal Equivalents Constructed from Cell Lines. *Science* 286(5447) 2169-2172
2. Gouveia RM, Connon, CJ (2016) Collagen Scaffolds for Corneal Regeneration. *Biomaterials and Regenerative Medicine in Ophthalmology*, Woodhead Publishing, Elsevier, 151e178
3. Connon CJ, Meek KM, Newton RH, Kenney MC, Karageozian H. (2000) Hyaluronidase Treatment, Collagen Fibril Packing and Normal Transparency in Rabbit Corneas. *J Refract Surg*, 16(4) 448-455
4. Connon CJ, Meek KM, Kinoshita S, Quantock AJ. (2004) Spatial and Temporal Variations in the Collagen Fibrillar Array During the Onset of Transparency in the Avian Cornea. *Exp Eye Res*, 78(5) 909-915
5. Connon CJ (2015) Approaches to Corneal Tissue Engineering: Top-down or Bottom-up? *Procedia Engineering*, 110 15-20
6. Gouveia RM, Castelletto V, Alcock SG, Hamley IW, Connon CJ (2013) Bioactive films produced from self-assembling peptide amphiphiles as versatile substrates for tuning cell adhesion and tissue architecture in serum-free conditions. *J Mat Chem B*, 1 6157-6169
7. Gouveia RM, Castelletto V, Hamley IW, Connon CJ (2015) New self-assembling multi-functional templates for the bio-fabrication and controlled self-release of cultured tissue. *Tissue Eng Pt A*, 21(11-12) 1772-1784
8. Gouveia RM, González-Andrades E, Cardona JC, González-Gallardo C, Ionescu AM, Garzon I, Alaminos M, González-Andrades M, Connon CJ (2016) Controlling the 3D architecture of Self-Lifting Auto-generated Tissue Equivalents (SLATEs) for optimized corneal graft composition and stability. *Biomaterials*, doi: 10.1016/j.biomaterials.2016.12.023
9. Meek KM, Leonard D, Connon CJ, Dennis S, Khan S. (2003) Transparency, swelling and scarring in the corneal stroma. *Eye*, 17(8) 927-936
10. Dvir T, Timko BP, Kohane DS, Langer R (2011) Nanotechnological strategies for engineering complex tissues. *Nat Nanotechnol*, 6 13-22
11. Swinehart T, Badylak SF (2016) Extracellular matrix bioscaffolds in tissue remodeling and morphogenesis. *Dev Dyn*, 245 351-360
12. Matsuura K, Utoh R, Nagase K, Okano T (2014) Cell sheet approach for tissue engineering and regenerative medicine. *J Controlled Release*, 190 228-239
13. Du Y, Lo E, Ali S, Khademhosseini A. (2008) Directed assembly of cell-laden microgels for fabrication of 3D tissue constructs. *Proc Natl Acad Sci*, 105 9522-9527
14. Gouveia, R.M., Koudouna, E., Jester, J., Figueiredo, F., Connon, C.J. (2017) Template Curvature Influences Cell Alignment to Create Improved Human Corneal Tissue Equivalents. *Advanced Biosystems* doi: 10.1002/adbi.201700135
15. Isaacson A, Swioklo S, Connon CJ. (2018) 3D bioprinting of a corneal stroma equivalent. *Exp Eye Res*. doi: 10.1016/j.exer.2018.05.010
16. Miotto M, Gouveia RM, Ionescu AM, Figueiredo F, Hamley IW, Connon CJ. (2019) 4D Corneal Tissue Engineering: Achieving Time-Dependent Tissue Self-Curvature through Localized Control of Cell Actuators. *Adv. Func. Mater.* doi: 10.1002/adfm.201807334
17. Gouveia RM, Lepert G, Gupta S, Mohan RR, Paterson C, Connon CJ. (2019) Assessment of corneal substrate biomechanics and its effect on epithelial stem cell maintenance and differentiation. *Nature Communications* In Press